



**ULTRATECH**  
INTERNATIONAL, INC



## Ultra- Spill Berm – Low Profile®

### Product Data Sheet

**Item Number:** 2052

**Item Name:** Ultra- Spill Berm – Low Profile®

**Containment Capacity:** 6.83 Gallons

Item #	Color	Misc. Features	Amount	Length	Width	Height	Weight
2052	Safety Orange	Interlocking end joints	1 Each	120" (3048mm)	2.25" (57.15mm)	1.375" (35mm)	13 Lbs. (5.89Kg)

**Description:** A non-absorbing urethane berm that forms a temporary bond with surfaces to stop leaks from spreading.

**Application:** For use in response to machine leaks and small chemical spills. They can be quickly deployed to contain the spill or leak preventing it from entering floor or storm drains until the spill or leak can be cleaned in accordance with local and state regulations.

**Product Features:** The Ultra- Spill Berm – Low Profile is an essential part of your spill response kit that can be quickly deployed to contain liquids from a spill or leak.

- 1 3/8" tall berm contains leaks, reduces slip hazards.
- Allows quick and easy clean up or recycling of liquids.
- Flexible urethane design will bend to follow any curve or angle needed.
- Inter locking end joints create longer lengths and are self-sealing.

**Composition:** 100% polyurethane.

**U.S. Patent No.:** 5,236,281

Material Specifications: 2025

<u>Specification</u>	<u>Value</u>	
Style	Low Profile	
Color	Safety Orange	
Dimensions	2.25"W/ 120"L/ 1.375"H	57.15mm/ 3048mm/ 35mm
Intended For	Smooth Surfaces	
Max Liquid Temp Exposure	225°F for up to 30 minutes	107.2°C for up to 30 minutes
Storage Temp Range	0°- 120°F	-17.7° - 48.8°C
Temperature Limit	0°- 160°F	-17.7° - 71.1°C
Sold As	1 each	
Weight	13lbs.	5.89kg.
Patent #	5,236,281	
National Stock Number (NSN)	7930-01-436-8320	
Qty Per Pallet	108	
Composition	Polyurethane	
UNSPSC	24101907	



**Chemical Compatibility for polyurethane**

Chemical	Swelling	Degradation	Grade
Acetone	2	0	D
Acetonitrile	1	0	C
Aluminum Salts	0	0	A
Barium Salts	0	0	A
Benzyl Alcohol	1	1	C
Boric Acid	0	0	A
Butanol	0	0	A
Calcium Chlorite	0	0	A
Carbon Disulfide	1	0	C
Cupric Chloride	0	0	A
Cyclohexanone	1	2	D
Dichloromethane	2	2	D
Diethylamine	1	1	C
Diethylformamide	2	2	D
Ethyl Acetate	1	0	C
Formaldehyde	0	0	A
Gasoline	0	0	A
Glycol Ether	0	0	A
Hexane	0	0	A
Hydrochloric Acid (37%)	0	2	D
Hydrogen Peroxide (30%)	1	0	C
Hydrofluoric Acid (48%)	0	2	D
Jet Fuel (JP-5)	0	0	A
Kerosene	0	0	A
Methanol	0	0	A
Methyl Ethyl Ketone	2	0	D
Mineral Oil	0	0	A
Naphtha	0	0	A
Nitrobenzene	0	2	D
Phenol	0	2	D
Propylene Glycol	0	0	A
Sodium Hydroxide (50%)	0	0	A
Sulfuric Acid (98%)	0	2	D
Sulfuric Acid (50%)	0	2	D
Tetrachloroethylene	0	0	A
Tetrahydrofuran	2	2	D
Toluene	1	0	C
1,1,1-Trichloroethane	1	0	C
Trichloroethylene	1	0	C
Triethylamine	0	0	A
Turpentine	0	0	A
Water	0	0	A



**KEY**

<b>Swelling</b>	<b>Degradation</b>	<b>Ratings</b>
Visually rated from 0-2;	Visually rated from 0-2;	NR (Not Recommended):
0 = none	0 = none	Significant degradation or swelling
1 = slight	1 = slight	FAIR: Slight swelling
2 = significant	2 = significant	GOOD: No swelling

**\*IMPORTANT USER NOTICE FOR BOTH THE POLYURETHANE & POLYETHYLENE CHEMICAL COMPATIBILITY GUIDES**

The data contained herein is a compilation of existing published data from leading manufacturers of polyurethane and does not represent actual testing performed by UltraTech International, Inc.

This listing is offered only as a guide and utilizes information which, to the best of UltraTech's knowledge, is accurate and reliable. Due to variables and conditions of application beyond the control of UltraTech, none of the data shown in this guide is to be construed as a guarantee, expressed or implied. UltraTech International, Inc. assumes no responsibility, obligation or liability in conjunction with the use or misuse of the information herein.